

Test Report

No. CANHG2009986601

Date: 30 Jun 2020

Page 1 of 4

SUN-FLY INT'L BUSINESS DEVELOPMENT LTD.

ROOM 2902, POLY MIDTOWN PLAZA, #23 XUANYUE EASTERN RD., HAIZHU DISTRICT, GUANGZHOU, CHINA, 510220

The following sample(s) was/were submitted and identified on behalf of the clients as : Sublimation Bamboo Cutting Board, 19.5*29*1.8cm

SGS Job No. : GZHL2006033699CW - GZ
 Tested Sample Info. : Style / Item No.: SW-BCB2029
 Client Ref. Info. : SW-BCB1720 Sublimation Bamboo Cutting Board, 16.5*19.5*1.8cm
 SW-BCB2033 Sublimation Bamboo Cutting Board, 19.5*33*1.8cm
 Date of Sample Received : 19 Jun 2020
 Testing Period : 19 Jun 2020 - 30 Jun 2020
 Test Requested : Selected test(s) as requested by client.
 Test Method : Please refer to next page(s).
 Test Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004–Sensorial examination odour and taste test	PASS
Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 – Specific Migration of Formaldehyde	PASS
Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 –Pentachlorophenol (PCP) content	PASS

Signed for and on behalf of
 SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Catty Gong

Catty Gong
 Approved Signatory

scan to see the report



CANHG2009986601



SGS-CSTC Standards Technical Services Co., Ltd.
 Guangzhou Branch Testing Center Chemical Laboratory.

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@sgs.com

198 Kezhu Road, Sciotech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075113 www.sgs.com.cn
 中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075113 e sgs.china@sgs.com

Test Report

No. CANHG2009986601

Date: 30 Jun 2020

Page 2 of 4

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	CAN20-099866.001	Brown bamboo board	Bamboo

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 – Sensorial examination odour and taste test

Test Method : With reference to DIN10955:2004,direct contact method.
No.of panelist:6

<u>Test Item(s)</u>	<u>Limit</u>	<u>001</u>
Test media	-	Cucumber
Test Temperature (°C)	-	40
Test time (hr)	-	2
Sensorial examination odour (Point scale)	2.5	2.0
Sensorial examination taste (Point scale)	2.5	2.0
Comment		PASS

Notes :

- Intensity scale (rounded at 0.5):
- 0 – no perceptible difference
 - 1 – just perceptible difference
 - 2 – slight difference
 - 3 – marked difference
 - 4 – strong difference

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 – Specific Migration of Formaldehyde

Test Method : With reference to EN13130-1:2004 for selection of test method, analysis was performed by UV-Vis.

Sample 001

Simulant Used : 3% Acetic Acid (W/V) Aqueous Solution
Test Condition : 70 °C 2.0 hr(s)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@sgs.com

Test Report

No. CANHG2009986601

Date: 30 Jun 2020

Page 3 of 4

<u>Test Item(s)</u>	<u>Max. Permissible</u> <u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>Test result</u>
Migration times	-	-	-	3rd
Area/Volume	-	dm ² /kg	-	6.0
Specific migration of Formaldehyde	15	mg/kg	0.1	4.2
Comment				PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
2. °C = Degree Celsius
3. MDL=Method Detection Limit
4. ND = Not Detected(less than MDL)
5. Visible color migration in simulatn

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 – Pentachlorophenol (PCP) content

Test Method : With reference to ISO 17070:2015, analysis was performed by GC-ECD or GC-MS.

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>001</u>
Pentachlorophenol(PCP)	0.15	mg/kg	0.05	ND
Comment				PASS

Notes :

1. mg/kg = milligram per kilogram
2. MDL=Method Detection Limit
3. ND = Not Detected(less than MDL)



Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

